

TOWN OF PRESQUE ISLE
CHIP SEAL DOUBLE COAT BID SPECIFICATIONS

The town is seeking a bid for Chip Sealing the following road per the double coat specifications.

Bartsch Road, Approximately .36 mile in length, 20 ft. wide, from E. Armour to its terminus.

All labor and equipment shall be furnished by the contractor.

Double Coat Specification:

First Coat Application

1. Final grade to be done by contractor.
2. Road to be watered and compacted with steel, vibrating roller.
3. CRS-2 or HFRS-2 Emulsion to be applied at full width and 170°.
4. 5/8" aggregate to be applied with a full width self-propelled distributor at a rate of .34 to .38 pounds per sq. yd.
5. Aggregate to be rolled with steel vibrating roller and pneumatic tired roller.

Second Coat Application:

1. Any loose material to be swept off before the second coat is applied.
2. Surface layer CRS-2 or HFRS-2 emulsion to be applied at .38 to .42 gallons per sq. yd. at 170° with a full width spray distributor.
3. 3/8" washed aggregate to be applied at .23 to .27 lbs. per sq. yd. with full-width self-propelled chip distributor.
4. To be rolled with at least four passes with a pneumatic tired roller.

Fog Seal

1. Sweep loose material off the road before seal is applied.
2. Provide CSS-1H-DL (1 to 1 with water) which shall meet the requirements of AASHTO-M208 without the use of a latex modification.
3. Seal shall be applied the full width of the road.

The Town of Presque Isle reserves the right to reject any or all proposals or to accept the proposal deem most advantageous to the town.